

Premi-Glas® 2103-22 CR-SX-HT

Thermoset, Unspecified

Premix, Inc.

Message:

Premi-Glas® 2103-22 CR-SX-HT is a fiberglass reinforced thermoset bulk molding compound for electrical and flame retardant applications.

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
Uses	Electrical/Electronic Applications		
UL File Number	E42524		
Forms	BMC - Bulk Molding Compound		
Physical	Nominal Value	Unit	
Specific Gravity	1.70 to 1.85	g/cm ³	
Molding Shrinkage - Flow	0.15 to 0.35	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12000	MPa	ASTM D638
Tensile Strength	38.0	MPa	ASTM D638
Flexural Modulus	10000	MPa	ASTM D790
Flexural Strength	124	MPa	ASTM D790
Poisson's Ratio	0.30		
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	430	J/m	ASTM D256
Unnotched Izod Impact	590	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
CLTE			
Flow ¹	2.5E-5	cm/cm/°C	
Transverse ²	3.5E-5	cm/cm/°C	
Thermal Conductivity	0.30	W/m/K	
RTI Elec	155	°C	UL 746
RTI Imp	160	°C	UL 746
RTI Str	160	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	15	kV/mm	ASTM D149
Arc Resistance	180	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (2.50 mm)	V-0		UL 94

Injection	Nominal Value	Unit
Mold Temperature	150	°C
Injection Pressure	3.50 to 6.50	MPa
NOTE		
1.	XY Direction	
2.	Z Direction	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

