

Kynar Flex® 3120-50

Polyvinylidene Fluoride

Arkema

Message:

KYNAR FLEX® 3120-50 is a pelletized semi-crystalline VF2 based copolymer. It can be molded or extruded and has a useful temperature range from -40°C - 150°C. KYNAR FLEX® 3120-50 has a UL RTI of 150°C

KYNAR FLEX® 3121-50 can be used in compounding for wire and cable as well as other extrusion applications.

KYNAR FLEX® 3121-50 is a specially designed powder used as a polymer process aid (PPA) for polyolefins. The use of KYNAR FLEX® 3120-50 or KYNAR FLEX 3121-50 at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

General Information			
Features	Semi Crystalline		
Uses	Wire & Cable Applications		
Forms	Pellets		
Processing Method	Compounding		
	Extrusion		
	Injection Molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.76 to 1.79	g/cm³	ASTM D792

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	65 to 70		ASTM D2240

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	24.1 to 34.5	MPa	
Break, 23°C	34.5 to 48.3	MPa	
Tensile Elongation (Break, 23°C)	300 to 550	%	ASTM D638
Flexural Modulus (23°C)	621 to 827	MPa	ASTM D790
Flexural Strength (23°C)	20.7 to 34.5	MPa	ASTM D790
Compressive Strength (23°C)	31.0 to 41.4	MPa	ASTM D695

Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	161 to 168	°C	ASTM D3418

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ¹ (20°C)	2.0E+14	ohms · cm	ASTM D257

Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (232°C, 100 sec^-1)	2000 to 2600	Pa · s	ASTM D3835

NOTE			
1.	65% R.H.		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT