Sylvin 8240-75UV Red 6281

Polyvinyl Chloride

Sylvin Technologies Incorporated

Message:

Sylvin 8240-75UV Red 6281 Is A Vinyl Compound Formulated For 60 Degree Wire Jacketing Applications. This Compound Contains An Ultra Violet Stabilizer.

General Information			
Additive	UV stabilizer		
Uses	Wire and cable applications		
	Wire sheath		
Appearance	Red		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	75		ASTM D2240
Shaw A, 10 seconds	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	13.8	MPa	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	56.9	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	60.0	°C	ASTM D794
Melting Temperature	163 - 174	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	23	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

