

TECHNO ABS 15 K6

Acrylonitrile Butadiene Styrene

Techno Polymer Co, Ltd.

Message:

TECHNO ABS 15 K6 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by injection molding and is available in Asia Pacific or North America. Primary characteristic: flame rated.

General Information			
Features	Laser Markable		
UL File Number	E54297		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	21	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.60	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	114		ASTM D785
R-Scale	113		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	53.9	MPa	ASTM D638
Yield	52.0	MPa	ISO 527-2
Flexural Modulus			
--	2920	MPa	ASTM D790
--	2490	MPa	ISO 178
Flexural Strength			
--	102	MPa	ASTM D790
--	81.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	13	kJ/m ²	ISO 179
Notched Izod Impact	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	96.0	°C	ASTM D648
0.45 MPa, Unannealed	82.0	°C	ISO 75-2/B
Flammability	Nominal Value	Test Method	
Flame Rating (ALL)	HB	UL 94	
Injection	Nominal Value	Unit	

Drying Temperature	80.0 to 90.0	°C
Drying Time	2.0 to 5.0	hr
Rear Temperature	190 to 260	°C
Middle Temperature	190 to 260	°C
Front Temperature	190 to 260	°C
Mold Temperature	40.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

