

Durethan® A 30 S FN31 000000

Polyamide 66

LANXESS Asia/Pacific

Message:

PA 66, non-reinforced, injection molding, halogen free flame retardant, improved flowability

General Information				
UL YellowCard		E245249-100600971	E245249-101386019	
Features		Halogen-free		
		Flame retardancy		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Resin ID (ISO 1043)		PA FR(30)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.17	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Vertical flow direction: 270°C, 2.00mm ¹	1.1	--	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.10	--	%	ISO 294-4
Flow direction: 270°C, 2.00mm ³	1.1	--	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.10	--	%	ISO 294-4
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3800	1500	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	85.0	50.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	4.1	> 20	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	3700	1600	MPa	ISO 178/A
Flexural Stress ⁶				
3.5% strain	120	40.0	MPa	ISO 178/A
23°C	125	55.0	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	5.8	7.8	%	
ISO Shortname	PA 66, GFHR, 12-040; ISO 1043-PA FR (30)			ISO 1874
Residual Moisture Content	0.030 - 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	< 10	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU

-30°C	50	80	kJ/m ²	ISO 179/1eU
23°C	60 kJ/m ²	No Break		ISO 179/1eU
Notched Izod Impact (23°C)	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	55	60	kJ/m ²	ISO 180/1U
23°C	55 kJ/m ²	No Break		ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	212	--	°C	ISO 75-2/B
1.8 MPa, not annealed	80.0	--	°C	ISO 75-2/A
Vicat Softening Temperature	230	--	°C	ISO 306/B120
Melting Temperature ⁸	265	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	8.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	7.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+14	1.0E+13	ohms · cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	30	25	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.00	8.00		IEC 60250
23°C, 1 MHz	4.00	4.00		IEC 60250
Dissipation Factor				IEC 60250
23°C, 100 Hz	0.012	0.20		IEC 60250
23°C, 1 MHz	0.019	0.055		IEC 60250
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.400 mm)	V-0	--		UL 94
Glow Wire Flammability Index (0.400 mm)	960	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (0.400 mm)	775	--	°C	IEC 60695-2-13
Oxygen Index ⁹	34	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 270		°C	

Mold Temperature	80.0 - 100	°C
NOTE		
1.	60x60x2; WZ 80°C; 600 Bar	
2.	60x60x2	
3.	60x60x2; WZ 80°C; 600 Bar	
4.	60x60x2	
5.	2.0 mm/min	
6.	2.0 mm/min	
7.	Pull Rate: 2 mm/min; 50% RH	
8.	10°C/min	
9.	Procedure A	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

