

HiPrene® MT41VD

Polypropylene

GS Caltex

Message:

HiPrene® MT41VD is a 15% mineral filled, impact modified polypropylene compound suitable for injection moulding. This material has been developed for highly demanding aesthetic automotive application, with perfect scratch resistance and UV stabilization. It is especially suitable for car interior applications requiring ductility, because of its high impact resistance and requiring very high scratch resistance because of location in the car interior. This grade is available in natural or color-matched, pellet form.

General Information			
Filler / Reinforcement	Mineral filler, 15% filler by weight		
Additive	Impact modifier UV stabilizer		
Features	Impact modification Rigidity, high Impact resistance, high Workability, good Scratch resistance ductility		
Uses	Application in Automobile Field Car interior parts		
Appearance	Available colors Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	12	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	0.90	%	Internal method
Flow direction	0.90	%	Internal method
Ash Content (600°C)	16	%	ISO 3451
Volatile Matter	0.10	%	Internal method
Anti-scratch-Delta L ¹	1.20		
Flammability	70	mm/min	TL 1010
Fogging ² (100°C)		mg	DIN 75201
Emission		g	VDA 277

Odor ³ (80°C)	2.40		
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	70		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	22.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	%	ISO 527-2
Flexural Modulus ⁴ (23°C)	1750	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	30	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	110	°C	ISO 75-2/B
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Hopper Temperature	40.0 - 80.0	°C	
Processing (Melt) Temp	210 - 250	°C	
Mold Temperature	30.0 - 50.0	°C	
Holding Pressure	4.00 - 6.50	MPa	
Injection instructions			
Back Pressure: Low to MediumScrew Speed: Low to MediumInjection Speed: 100 to 200 m/min			
NOTE			

- | | |
|----|---|
| 1. | Performed on black plaques with rough structure, acc. PV 3952 |
| 2. | 16 hr |
| 3. | 2 hr, acc. PV 3900 |
| 4. | 2.0 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT