

TAFMER™ A-20090

Polyalphaolefin
Mitsui Chemicals America, Inc.

Message:
TAFMER™ A- 20090 is a polyα-olefin (PAO) material. This product is available in North America.

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.890	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	18	g/10 min	ASTM D1238
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Vicat Softening Temperature	60.0	°C	ASTM D1525
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms·cm	ASTM D257
Dielectric Strength	55	kV/mm	ASTM D149
Dielectric Constant	2.10		ASTM D150
Dissipation Factor	1.3E-4		ASTM D150
Additional Information			

Tensile Strength @ Break, JIS K 6301: 160 kgf/cm²Elongation @ Break, JIS K 6301: 750%Surface Hardness, JIS K 6301, A Scale: 86

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

