

TECACOMP® PA46 TF30 natural 3148

Polyamide 46
Ensinger GmbH

Message:

TECACOMP® PA46 TF30 natural 3148 is a polyamide 46 (nylon 46) product containing 30% ptfe fiber. It can be processed by injection molding and is available in Europe.

General Information			
Filler / Reinforcement	PTFE fiber, 30% filler by weight		
Appearance	Natural color		
Forms	Particles		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm³	
Apparent Density	0.77	g/cm³	ISO 60
Viscosity Number (H2SO4 (Sulphuric Acid))	185	cm³/g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/50
Tensile Stress	65.0	MPa	ISO 527-2/50
Tensile Strain (Break)	8.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	45	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	75.0	°C	DIN 53765
Melting Temperature	295	°C	DIN 53765
Service Temperature			
long term	130	°C	
short term	220	°C	
Injection	Nominal Value	Unit	
Drying Temperature	80 - 90	°C	
Drying Time	2.0 - 8.0	hr	
Suggested Max Moisture	0.050	%	
Processing (Melt) Temp	280 - 320	°C	
Mold Temperature	80 - 150	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

