

Dynacom 602-G20

Acrylonitrile Styrene Copolymer

Dynachem Co. Ltd.

Message:

Dynacom 602-G20 is an Acrylonitrile Styrene Copolymer (AS) material. It is available in Asia Pacific. Primary attribute of Dynacom 602-G20: Flame Rated.

General Information			
UL YellowCard	E164708-224857		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (240°C/10.0 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow ¹	0.30 to 0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	> 0.35	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²	103	MPa	ASTM D638
Tensile Elongation ³ (Break)	4.0	%	ASTM D638
Flexural Modulus ⁴	6370	MPa	ASTM D790
Flexural Strength ⁵	123	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	100	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
NOTE			
1.	Thickness: 2 to 3 mm		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	3.0 mm/min		
5.	3.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

