

Romiloy® 1015

Polycarbonate + ABS

ROMIRA GmbH

Message:

Romiloy® 1015 is a polycarbonate acrylonitrile butadiene styrene (PC ABS) material. This product is available in Europe and is processed by extrusion or injection molding.

Romiloy® The main features of the 1015 are:

flame retardant/rated flame

Heat resistance

General Information	
Features	Heat resistance, high
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.15	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	17	g/10 min	ISO 1133
Molding Shrinkage (23°C)	0.40 - 0.70	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.20	%	ISO 62

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2200	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	55.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	130	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2000	MPa	ISO 178
Flexural Stress ² (23°C)	85.0	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	42	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	110	°C	ISO 75-2/A
Vicat Softening Temperature	138	°C	ISO 306/B50
CLTE - Flow (23 to 55°C)	8.5E-5	cm/cm/°C	ISO 11359-2

Flammability	Nominal Value	Test Method
Flame Rating (1.60 mm)	HB	UL 94

Additional Information	
------------------------	--

The value listed as Molding Shrinkage ISO 294-4, was tested in accordance with DIN 16901. The value listed as Coefficient of Linear Thermal Expansion ISO 11359-1-2, was tested in accordance with DIN 53752.

Injection	Nominal Value	Unit
Drying Temperature	< 100	°C

Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.050	%
Suggested Max Regrind	5	%
Processing (Melt) Temp	240 - 270	°C
Mold Temperature	80.0	°C
Injection Rate	Moderate-Fast	
Extrusion	Nominal Value	Unit
Drying Temperature	80.0 - 100	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	< 0.050	%
Cylinder Zone 1 Temp.	210 - 250	°C
Cylinder Zone 2 Temp.	210 - 250	°C
Cylinder Zone 3 Temp.	210 - 250	°C
Cylinder Zone 4 Temp.	210 - 250	°C
Cylinder Zone 5 Temp.	210 - 250	°C
Melt Temperature	< 260	°C
NOTE		
1.	2.0 mm/min	
2.	2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

