

VAMPAMID 66 3054 V0

Polyamide 66

Vamp Tech

Message:

UL 94 V0, 30% mixed glass fiber and mineral filled, excellent dimensional stability, good thermal and electrical features.

General Information			
UL YellowCard	E140692-223038		
Filler / Reinforcement	Glass\Mineral,30% Filler by Weight		
Features	Good Dimensional Stability		
	Good Electrical Properties		
	Good Thermal Stability		
Uses	Electrical/Electronic Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ASTM D638
Tensile Strength (Yield)	100	MPa	ASTM D638
Tensile Elongation (Break)	2.2	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	4.5	kJ/m²	ISO 180/A
Unnotched Izod Impact Strength	35	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	215	°C	ASTM D648A
Vicat Softening Temperature	225	°C	ASTM D1525 ¹
RTI Elec	140	°C	UL 746
RTI Imp	140	°C	UL 746
RTI Str	140	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index (1.00 to 2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.00 to 2.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	

Drying Time	3.0	hr
Processing (Melt) Temp	275	°C
Mold Temperature	100	°C

NOTE

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

