

Jam HDPE HM8355

High Density Polyethylene
Jam Petrochemical Company

Message:

Jam HDPE HM8355 is a High Density Polyethylene product. It can be processed by blow molding and is available in Africa & Middle East.

General Information			
Uses	Blow Molding Applications		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.951 to 0.955	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.3 to 9.7	g/10 min	ISO 1133
Flow Rate Ratio ¹	24.0 to 30.0		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C, Compression Molded)	> 10	kJ/m ²	ISO 179/1eA
NOTE			

1.

5/2.16, FRR values are statistical and calculated by dividing MFR values.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

