

LEXAN™ HFD4471 resin

Polycarbonate

SABIC Innovative Plastics

Message:

LEXAN HFD4471 is a 10% glass filled, medium flow, impact modified, injection moldable grade designed for high flow and superior surface appearance. HFD4417 has enhanced mold release, impact ductility and broad color space.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Additive	Impact modifier demoulding		
Features	Medium liquidity Good appearance ductility		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.26	g/cm ³	ASTM D792
--	1.25	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	9.00	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	0.30 - 0.40	%	Internal method
Transverse flow: 3.20mm	0.40 - 0.50	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.14	%	ISO 62
Equilibrium, 23°C, 50% RH	0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	3700	MPa	ASTM D638
Tensile Strength			
Yield ²	54.0	MPa	ASTM D638
Yield	58.0	MPa	ISO 527-2/5
Fracture ³	37.0	MPa	ASTM D638
Fracture	41.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	3.0	%	ASTM D638
Yield	3.0	%	ISO 527-2/5

Fracture	10	%	ISO 527-2/5
Flexural Modulus ⁵ (50.0 mm Span)	3300	MPa	ASTM D790
Flexural Strength ⁶ (Yield, 50.0 mm Span)	95.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁷			ISO 179/1eA
-30°C	10	kJ/m ²	ISO 179/1eA
23°C	29	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ⁸			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
23°C	290	J/m	ASTM D256
-30°C ⁹	13	kJ/m ²	ISO 180/1A
23°C ¹⁰	30	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	2100	J/m	ASTM D4812
-30°C ¹¹	93	kJ/m ²	ISO 180/1U
23°C ¹²	180	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	43.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 3.20mm	131	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	125	°C	ASTM D648
Vicat Softening Temperature	135	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 40°C	4.0E-5	cm/cm/°C	ASTM E831
Flow: 23 to 80°C	4.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	7.0E-5	cm/cm/°C	ASTM E831
Lateral: 23 to 80°C	8.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI	80.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (0.400 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	48	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	

Rear Temperature	266 - 288	°C
Middle Temperature	277 - 299	°C
Front Temperature	288 - 310	°C
Nozzle Temperature	282 - 304	°C
Processing (Melt) Temp	288 - 310	°C
Mold Temperature	71.1 - 93.3	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Vent Depth	0.025 - 0.076	mm

NOTE

1.	5.0 mm/min
2.	Type 1, 5.0 mm/min
3.	Type 1, 5.0 mm/min
4.	Type 1, 5.0 mm/min
5.	1.3 mm/min
6.	1.3 mm/min
7.	80*10*3 sp=62mm
8.	80*10*3 sp=62mm
9.	80*10*3
10.	80*10*3
11.	80*10*3
12.	80*10*3

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT