

E-RIALGLASS H 07 H 30 G

Polypropylene Homopolymer
RIALTI Srl

Message:

Polypropylene homopolymer obtained by partial recycling of selected industrial scraps; 30% glass fiber chemically coupled; heat stabilized for prolonged exposure to high temperatures. Good mechanical properties
High flowabilitylevel, specific for injection molding; available in versions black colore.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Chemically Coupled		
	Heat Stabilized		
	High Flow		
	Homopolymer		
Appearance	Black		
Forms	Regrind		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	0.30	%	
Ash Content	30	%	ISO 3451
Accelerated Oven Aging (150°C)	1.4	month	ISO 4577
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	80.0	MPa	ISO 527-2/20
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2/20
Flexural Modulus ¹ (23°C)	5700	MPa	ISO 178
Flexural Stress (23°C)	105	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	34	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength			ISO 180/1A
-20°C	6.0	kJ/m ²	
23°C	8.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	139	°C	ISO 75-2/A
Vicat Softening Temperature	124	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		IEC 335
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	200 to 240	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Rate	Fast		
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT