

Lotrène® LLDPE Q2018N

Linear Low Density Polyethylene

QATOFIN Company Limited

Message:

Lotrène® Q2018 Series are Linear Low Density Polyethylene resins produced in a gas phase reactor using butene (C4) co-monomer.

They are designed for blown film applications and can be used in pure form as well as blended with other PE resins, such as LDPE or HDPE and mPE resins for mono extrusion or co-extrusion process to modify film properties.

Lotrène® Q2018 Series are suited for many applications in the field of consumer, industrial, food or hygiene packaging such as freezer film, bread bags, shoppers and bags as well as lamination film and multilayer packaging film.

General Information			
Additive	heat stabilizer		
Features	Butene comonomer		
	Thermal Stability		
Uses	Packaging		
	Thin wall packaging		
	Films		
	Laminate		
	Bags		
	Multilayer film		
	Industrial application		
	Mixing		
	Food packaging		
	Consumer goods application field		
Processing Method	Film extrusion		
	Blow film		
	Co-extruded film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD: 40 µm, blown film	215	MPa	ASTM D882
1% secant, TD: 40 µm, blown film	245	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield, 40 µm, blown film	11.0	MPa	ASTM D882
TD: Yield, 40 µm, blown film	11.0	MPa	ASTM D882
MD: Broken, 40 µm, blown film	35.0	MPa	ASTM D882

TD: Broken, 40 μm, blown film	32.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 40 μm, blown film	850	%	ASTM D882
TD: Broken, 40 μm, blown film	900	%	ASTM D882
Dart Drop Impact ¹ (40 μm, Blown Film)	130	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 40 μm, blown film	220	g	ASTM D1922
TD: 40 μm, blown film	420	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	100	°C	ASTM D1525
Peak Crystallization Temperature (DSC)	121	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 40.0 μm, Blown Film)	55		ASTM D2457
Haze (40.0 μm, Blown Film)	14	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	170 - 210	°C	
Cylinder Zone 2 Temp.	170 - 210	°C	
Cylinder Zone 3 Temp.	170 - 210	°C	
Cylinder Zone 4 Temp.	170 - 210	°C	
Cylinder Zone 5 Temp.	170 - 210	°C	
Melt Temperature	190	°C	
Extrusion instructions			
Blow-up ratio: 2:1 to 3:1Die gap: >1.8 mm			
NOTE			
1.	F50		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT