## ISORENE<sup>™</sup> SA7-1001

## Thermoplastic Elastomer

SABIC Innovative Plastics Europe

## Message:

ISORENE SA7-1001 is a special compound in a natural opaque color for technical applications. The value listed as Strain at Break, ISO 527, was tested in accordance with ISO 37. The value listed as Stress at Break, ISO 527, was tested in accordance with ISO 37.

| General Information      |                   |       |             |
|--------------------------|-------------------|-------|-------------|
| Appearance               | Natural Color     |       |             |
|                          | Opaque            |       |             |
|                          |                   |       |             |
| Forms                    | Pellets           |       |             |
| Processing Method        | Injection Molding |       |             |
| Physical                 | Nominal Value     | Unit  | Test Method |
| Density                  | 1.24              | g/cm³ | ISO 1183    |
| Hardness                 | Nominal Value     | Unit  | Test Method |
| Shore Hardness (Shore A) | 71                |       | ISO 868     |
| Mechanical               | Nominal Value     | Unit  | Test Method |
| Tensile Stress (Break)   | 5.00              | MPa   | ISO 527-2   |
| Tensile Strain (Break)   | 550               | %     | ISO 527-2   |
| Elastomers               | Nominal Value     | Unit  | Test Method |
| Tear Strength            | 23                | kN/m  | ISO 34-1    |
| Compression Set          |                   |       | ISO 815     |
| 23°C, 70 hr              | 20                | %     |             |
| 70°C, 22 hr              | 80                | %     |             |
| 100°C, 22 hr             | 95                | %     |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

