

LONGLITE® TPEE 1155LL

Thermoplastic Polyester Elastomer

CCP Group

Message:

1155LL is medium modulus grade with nominal Durometer hardness of 55D. It contains non-discolour stable antioxidants. It can be processed by thermoplastic processing techniques like injection molding and extrusion molding grade.

CHARACTERISTICS

1. Excellent medium modulus for injection and extrusion molding grade.
2. Excellent flexibility and fatigue resistance.
3. Excellent creep resistance.
4. Excellent low shrinkage and higher melting temperature

General Information			
Additive	Antioxidation		
Features	Antioxidation		
	Good creep resistance		
	Good flexibility		
	Good color stability		
	Fatigue resistance		
	Low shrinkage		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30	g/10 min	ISO 1133
Molding Shrinkage	0.65	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.40	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	40.0	MPa	ISO 527-2
Tensile Strain (Break)	500	%	ISO 527-2
Flexural Modulus	190	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	No Break		ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	65.0	°C	ISO 75-2/B

1.8 MPa, not annealed	45.0	°C	ISO 75-2/A
Melting Temperature (DSC)	204	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.6E+13	ohms	IEC 60093
Volume Resistivity	2.1E+13	ohms·cm	IEC 60093
Dielectric Strength (2.00 mm)	17	kV/mm	IEC 60243-1
Injection	Nominal Value	Unit	
Drying Temperature	105	°C	
Drying Time	3.0 - 5.0	hr	
Suggested Max Moisture	< 0.10	%	
Rear Temperature	210 - 230	°C	
Middle Temperature	220 - 250	°C	
Front Temperature	220 - 250	°C	
Nozzle Temperature	220 - 250	°C	
Processing (Melt) Temp	204	°C	
Mold Temperature	20.0 - 50.0	°C	
Injection Pressure	29.4 - 98.1	MPa	
Holding Pressure	4.90 - 39.2	MPa	
Screw Speed	40 - 80	rpm	
Injection instructions			

Injection time: 2 to 10 secHolding pressure time: 10 to 30 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT