

Mirathane™ E95

Thermoplastic Polyurethane Elastomer (Polyester)

Miracll Chemicals Co., Ltd.

Message:

Mirathane™ E95 is a Thermoplastic Polyurethane Elastomer (Polyester) (TPU-Polyester) product. It is available in Asia Pacific.

Characteristics include:

Chemical Resistant

Wear Resistant

General Information			
Features	Good Abrasion Resistance		
	Hydrolysis Resistant		
	Low Compression Set		
	Oil Resistant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	95		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Abrasion Loss	35.0	mm ³	DIN 53516
Service Temperature	-20 to 90	°C	
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	13.0	MPa	
300% Strain	26.0	MPa	
Tensile Strength (Yield)	40.0	MPa	ASTM D412
Tensile Elongation (Break)	350	%	ASTM D412
Tear Strength	120	kN/m	ASTM D624
Compression Set			ASTM D395
70°C, 22 hr	30	%	
100°C, 24 hr	40	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ¹	-30.0	°C	DSC
Extrusion	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0 to 4.0	hr	
Cylinder Zone 1 Temp.	210	°C	
Cylinder Zone 2 Temp.	205	°C	
Cylinder Zone 3 Temp.	200	°C	
Die Temperature	215	°C	

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

