

Armlen® PP TM 15-1APK

Polypropylene

Poly Plastic

Message:

Armlen® PP TM 15-1APK is a Polypropylene product. It is available in Europe.

General Information		
Physical	Nominal Value	Unit
Density	1.30	g/cm ³
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.2 to 3.5	g/10 min
Molding Shrinkage	0.70 to 0.90	%
Mechanical	Nominal Value	Unit
Tensile Stress (Yield)	23.0	MPa
Flexural Modulus (23°C)	1900	MPa
Flexural Stress	30.0	MPa
Impact	Nominal Value	Unit
Charpy Unnotched Impact Strength		
-40°C	25	kJ/m ²
20°C	No Break	
Thermal	Nominal Value	Unit
Heat Deflection Temperature		
0.45 MPa, Unannealed	105	°C
1.8 MPa, Unannealed	55.0	°C
Melting Temperature	162	°C
Electrical	Nominal Value	Unit
Surface Resistivity ¹	1.0E+15	ohms
Volume Resistivity ²	1.0E+17	ohms·cm
Electric Strength ³	27	kV/mm
Flammability	Nominal Value	Unit
Glow Wire Ignition Temperature	960	°C
Additional Information	Nominal Value	Unit
Burn Resistant Category	PX-0	
Trekingostoykost (KIT)	14000	mm
NOTE		
1.	Dry	
2.	Dry	
3.	Dry	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT