

# Teflon® PFA TE9724

Perfluoroalkoxy  
DuPont Fluoropolymers

## Message:

For inventory control purposes product name may be followed by an X.  
Products labeled PFA TE9724 and PFA TE9724 X are equivalent and all information in this document is applicable to both.

### Typical Application

DuPont™ Teflon ® PFA TE9724 is an ideal resin for applications involving compounding and compression molding, as well as extruded tubing and other profiles for hose, electrical insulators, and sleeving; industrial film and products made from film; and injection or compression molded articles requiring superior electrical, chemical, and thermal properties. Teflon ® PFA TE9724 offers a slightly higher melt flow rate than Teflon ® PFA TE9725, providing greater processing ease.

### Description

DuPont™ Teflon ® PFA TE9724 is a general-purpose fluoroplastic resin available as loosely compacted fluff. It is intended for use in special application processes in consultation with DuPont. Compared with other grades of Teflon ® PFA, its most unique features are a relatively high flow rate and properties that make it suitable for a variety of processes and demanding end uses, especially compounding and compression molding. Table 1 shows the typical property data for Teflon ® PFA TE9724.

Teflon ® PFA TE9724 is used when traditional extrusion and molding processes are required for producing products with the superior properties of a fluoroplastic resin. Compared to other thermoplastics, the high melt strength and thermal stability of Teflon ® PFA TE9724 can be used to improve processing rates. Compared with other thermoplastics, Teflon ® PFA TE9724 provides a superior balance and level of end-use properties at high service temperatures. Teflon ® PFA TE9724 combines the processing ease of conventional thermoplastics with many properties similar to those of polytetrafluoroethylene.

Properly processed products made from neat Teflon ® PFA TE9724 resin provide the superior properties characteristic of fluoroplastic resins: chemical inertness, exceptional dielectric properties, heat resistance, toughness and flexibility, low coefficient of friction, non-stick characteristics, negligible moisture absorption, low flammability, performance at temperature extremes and excellent weather resistance.

In a flame situation, products of Teflon ® PFA TE9724 resist ignition and do not promote flame spread. When ignited by flame from other sources, their contribution of heat is very small and added at a slow rate with very little smoke.

Teflon ® PFA TE9724 meets the requirements of ASTM D3307, Type I

General Information	
Features	Low friction coefficient
	Low hygroscopicity
	Low smoke
	Good electrical performance
	Good melt strength
	Good flexibility
	High liquidity
	Good chemical resistance
	Good weather resistance
	Heat resistance, medium
	Thermal stability, good
	Good toughness
Uses	Films
	Lining
	Electrical/Electronic Applications
	Composite
	Pipe

Pipe fittings

Profile

Forms	Fluff
Processing Method	Composite
	Extrusion
	Resin transfer molding
	Compression molding
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.14	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (372°C/5.0 kg)	12	g/10 min	ASTM D3307, ISO 12086
Water Absorption (24 hr)	< 0.030	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	25.0	MPa	ASTM D3307, ISO 12086
Tensile Elongation (Break, 23°C)	300	%	ASTM D3307, ISO 12086
Flexural Modulus (23°C)	590	MPa	ASTM D790, ISO 178
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	305	°C	ASTM D4591
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms · cm	ASTM D257, ISO 1325
Dielectric Strength			
0.250 mm <sup>1</sup>	80	kV/mm	ASTM D149
0.250 mm	80	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	2.03		ASTM D150, IEC 60250
Dissipation Factor (1 MHz)	< 2.0E-4		ASTM D150, IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating <sup>2</sup>	V-0		UL 94
Oxygen Index	> 95	%	ASTM D2863, ISO 4589-2
Additional Information	Nominal Value	Unit	Test Method
MIT Folding Endurance <sup>3</sup> (200.0 µm)	1.5E+4	Cycles	ASTM D2176

Weather and Chemical Resistance: Outstanding

#### NOTE

1. Method A (short time)  
  
These results are based on laboratory tests under controlled conditions and do not reflect performance under actual fire conditions, current rating is a typical theoretical value.
- 2.

3. Depending on fabrication conditions

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

