

megol® CA 55 SV/P1

Styrene Ethylene Butylene Styrene Block Copolymer

API SpA

Message:

megol® CA 55 SV/P1 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It can be processed by calendering and is available in Europe. Applications of megol® CA 55 SV/P1 include conveyors, fabrics/fibers and industrial applications.

Characteristics include:

RoHS Compliant

Eco-Friendly/Green

General Information			
Features	Recyclable Material		
Uses	Conveyors		
	Industrial Applications		
	Textile Applications		
RoHS Compliance	RoHS Compliant		
Processing Method	Calendering		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	8.00	MPa	
100% Strain	1.60	MPa	
300% Strain	3.10	MPa	
Tensile Elongation (Break)	640	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	26.0	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	2.0	hr	
NOTE			
1.	Without Notch		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

