

Karina WHITE PVC COMPOUND

818-10/121-AY-ERYB

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

LEAD STABILIZED PVC COMPOUND RECOMMENDED FOR EXTRUSION OF PROFILES FOR GENERAL APPLICATIONS. IT IS SUPPLIED IN PELLET FORM AND SHOULD BE PROCESSED AT THE TEMPERATURE RANGE OF 170C TO 190C.

General Information			
Additive	Lead Stabilizer		
Uses	Profiles		
Appearance	White		
Forms	Pellets		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.49 to 1.55	g/cm ³	ASTM D792
Ash Content	< 8.9	%	NBR 14295
Color a	-1.73 to -0.130		ME 12
Color b	-2.68 to -1.08		ME 12
Color L	90.1 to 91.7		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	78 to 82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 39.2	MPa	ASTM D638
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT