

Argothane® SS-4031-85

Thermoplastic Polyurethane Elastomer

Argotec LLC

Message:

Applications:

Lamination

Characteristics:

Excellent melt flow during lamination

General Information			
Features	Good Flow		
Uses	Laminates		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	55.2	MPa	ASTM D638
Tensile Elongation (Break)	480	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D638
100% Strain	6.90	MPa	
300% Strain	17.2	MPa	
Tear Strength ¹	87.5	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	145 to 160	°C	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT