

Durethan® BKV 30 N1 000000

Polyamide 6

LANXESS Corporation

Message:

PA 6, 30 % glass fibers, injection molding, flame retardant

General Information				
UL YellowCard		E245249-473592		
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		Flame retardancy		
Features		Flame retardancy		
Agency Ratings		EC 1907/2006 (REACH)		
Forms		Particle		
Processing Method		Injection molding		
Resin ID (ISO 1043)		PA GF FR (22)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.58	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.60	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.12	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.22	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.040	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	5.1	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	11700	6500	MPa	ISO 527-2/1
Tensile Stress				
Yield, 23°C	--	80.0	MPa	ISO 527-2/50
Fracture, 23°C	140	80.0	MPa	ISO 527-2/5
Tensile Strain				
Yield, 23°C	--	3.5	%	ISO 527-2/50
Fracture, 23°C	2.0	3.6	%	ISO 527-2/5
Nominal Tensile Strain at Break (23°C)	--	4.0	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	11000	7500	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	230	145	MPa	ISO 178/A

Flexural Strain at Flexural Strength ⁷ (23°C)	2.5	3.5	%	ISO 178/A
ISO Shortname	PA 6, GFR, 14-120, GF30	--		ISO 1874
Residual Moisture Content	0.030 - 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°C	< 10	< 10	kJ/m ²	ISO 179/1eA
-30°C	< 10	< 10	kJ/m ²	ISO 179/1eA
23°C	12	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	45	kJ/m ²	ISO 179/1eU
23°C	60	55	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-40°C	< 10	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	50	45	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	5.00	--	J	ISO 6603-2
23°C	7.00	9.00	J	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	220	--	°C	ISO 75-2/B
1.8 MPa, not annealed	205	--	°C	ISO 75-2/A
8.0 MPa, not annealed	135	--	°C	ISO 75-2/C
Vicat Softening Temperature	> 200	--	°C	ISO 306/B50, ISO 306/B120
Melting Temperature ⁸	225	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+14	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+14	1.0E+13	ohms·cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	28	27	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.70	8.00		IEC 60250
23°C, 1 MHz	4.20	4.50		IEC 60250
Dissipation Factor				IEC 60250

23°C, 100 Hz	0.013	0.13		IEC 60250
23°C, 1 MHz	0.019	0.045		IEC 60250
Comparative Tracking Index				IEC 60112
Solution a ⁹	350	--	V	IEC 60112
Solution B ¹⁰	125	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	V-1	--		UL 94
3.20 mm	V-0	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
2.00 mm	960	--	°C	IEC 60695-2-12
3.00 mm	960	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature				IEC 60695-2-13
1.60 mm	775	--	°C	IEC 60695-2-13
3.00 mm	775	--	°C	IEC 60695-2-13
Oxygen Index ¹¹	32	--	%	ISO 4589-2
Injection	Dry	Unit		Test Method
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	240 - 260		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			
9.	Erosion depth: 0.300mm			
10.	Erosion depth: 0.200mm			
11.	Procedure A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

