

# Gallonprene® GP210-7510

Thermoplastic Elastomer

Shenzhen Sungallon Rubber & Plastic Corporation Limited

## Message:

Gallonprene® GP210-7510 is a thermoplastic elastomer (TPE) product. It can be processed by injection molding and is available in Africa and the Middle East, Latin America or Asia Pacific. Gallonprene® GP210-7510 application areas include engineering/industrial accessories, containers and handles.

Features include:

Comply with REACH standard

ROHS certification

chemical resistance

Halogen-free

General Information			
Features	Good chemical resistance		
	Halogen-free		
Uses	O-rings		
	overmolding		
	Container		
	Soft handle		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Translucent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.868	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/2.16 kg)	1.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 23°C)	75		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Break)	12.8	MPa	ASTM D412
Tensile Elongation <sup>2</sup> (Break)	600	%	ASTM D412
Injection	Nominal Value	Unit	
Rear Temperature	145 - 165	°C	
Middle Temperature	155 - 175	°C	
Front Temperature	165 - 185	°C	
Processing (Melt) Temp	115 - 135	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection Rate	Fast		
Injection instructions			

Processing Temperature Limit: 260°CInjection Pressure: HighBack Pressure: 20 to 50%Overmolding Parameters:Rear Temperature: 165 to 185°CCenter Temperature: 175 to 195°CFront Temperature: 185 to 205°CMelt Temperature: 115 to 135°C Mold Temperature: 30 to 60°CProcessing Temperature Limit: 260°CInjection Pressure: HighInjection Speed: HighBack Pressure: 20 to 50%

NOTE

- |    |            |
|----|------------|
| 1. | 500 mm/min |
| 2. | 500 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

