

VYLOPET® CA3300

Polycarbonate + PBT

TOYOBO America, Inc.

Message:

VYLOPET® CA3300 is a Polycarbonate + PBT (PC+PBT) product. It is available in North America. Typical application: Appliances.

Characteristics include:

- Flame Rated
- Chemical Resistant
- Good Aesthetics
- Impact Resistant

General Information			
Features	Good Chemical Resistance		
	Good Impact Resistance		
	Good Surface Finish		
Uses	Appliance Components		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.00 mm)	0.70	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	66.0	MPa	ASTM D638
Tensile Elongation (Break)	140	%	ASTM D638
Flexural Modulus	2600	MPa	ASTM D790
Flexural Strength (Yield)	96.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	82	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	125	°C	
1.8 MPa, Unannealed	112	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	270	°C	
Mold Temperature	70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

