

LNP™ LUBRICOMP™ RKN14 compound

Polyamide 66

SABIC Innovative Plastics Europe

Message:

LNP LUBRICOMP RKN14 is a compound based on Nylon 66 resin containing Mineral, MOS2.

Also known as: LNP* LUBRICOMP* Compound RML4214S

Product reorder name: RKN14

General Information			
Filler / Reinforcement	Mineral		
Additive	Molybdenum Disulfide Lubricant		
Features	Lubricated		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.34	g/cm ³	ISO 1183
Molding Shrinkage - Flow ¹	0.70 to 0.90	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6300	MPa	ISO 527-2/1
Tensile Stress (Break)	77.0	MPa	ISO 527-2/5
Tensile Strain (Break)	4.2	%	ISO 527-2/5
Flexural Modulus ²	5000	MPa	ISO 178
Flexural Stress	111	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ³ (23°C)	6.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁴ (23°C)	50	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁵ (1.8 MPa, Unannealed, 64.0 mm Span)	104	°C	ISO 75-2/Af
NOTE			
1.	Tensile Bar		
2.	2.0 mm/min		
3.	80*10*4		
4.	80*10*4		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

