

HAIPLEN H90 C6

Polypropylene Homopolymer

Taro Plast S.p.A.

Message:

HAIPLEN H90 C6 is a polypropylene homopolymer (PP Homopoly) product, which contains 30% calcium carbonate filler. It can be processed by injection molding and is available in Europe.

- Features include:
- flame retardant/rated flame
 - high liquidity
 - Homopolymer
 - Antistatic
 - beautiful

General Information			
Filler / Reinforcement	Calcium carbonate filler, 30% filler by weight		
Additive	Antistatic property		
	heat stabilizer		
	UV stabilizer		
Features	Homopolymer		
	Antistatic property		
	High liquidity		
	Thermal Stability		
	Excellent appearance		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	1.1	%	ASTM D955
Transverse flow	1.1	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	35	%	ASTM D638, ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	30	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	120	°C	ASTM D648, ISO 75-2/B

1.8 MPa, not annealed	60.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature			
--	145	°C	ASTM D1525, ISO 306/A50 1 ¹
--	85.0	°C	ASTM D1525, ISO 306/B50 2 ²
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	HB		UL 94
Oxygen Index	21	%	ASTM D2863
Additional Information			
Granule Humidity, TARO 002: 0.05%Notched Izod Impact Strength , ISO 180, 23°C: 30 J/mCTI IEC 112, IEC 60112, Method A: >600 V			
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 80.0	°C	
Drying Time	1.0	hr	
Processing (Melt) Temp	190 - 220	°C	
Mold Temperature	40.0 - 60.0	°C	
Injection Rate	Fast		
NOTE			
1.	速率 A (50°C/h), 压 力1 (10N)		
2.	速率 A (50°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

