

# SABIC® STAMAX 60YM240 resin

Polypropylene  
SABIC Innovative Plastics

Message:

SABIC® STAMAX 60YM240 is a 60% long glass fiber reinforced polypropylene concentrate, specially developed for dilution with SABIC® PP homopolymer. The glass fibers are chemically coupled to the PP matrix, resulting in high stiffness and strength. The IMDS is 16501821.

General Information			
Filler / Reinforcement	Long glass fiber, 60% filler by weight		
Features	Rigidity, high		
	High strength		
	Chemical coupling		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm³	ISO 1183
Additional Information	Nominal Value	Unit	Test Method
Glass Fiber Content	60	%	ISO 3451
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	2.0	hr	
Rear Temperature	230 - 290	°C	
Middle Temperature	225 - 285	°C	
Front Temperature	220 - 280	°C	
Nozzle Temperature	220 - 280	°C	
Processing (Melt) Temp	220 - 280	°C	
Mold Temperature	20.0 - 80.0	°C	
Back Pressure	0.00 - 0.500	MPa	
Injection instructions			

Screw Speed: Lowest Possible

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT