

Geon™ HTX M6230

Polyvinyl Chloride Alloy

PolyOne Corporation

Message:

Geon™ HTX M6230 is a Polyvinyl Chloride Alloy (PVC Alloy) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ HTX M6230 include appliances, business/office goods, construction applications, electrical/electronic applications and wire & cable.

Characteristics include:

- Flame Rated
- High Flow
- Impact Resistant

General Information			
UL YellowCard	E41877-234301		
Features	General Purpose		
	High Flow		
	Medium Impact Resistance		
Uses	Appliances		
	Business Equipment		
	Construction Applications		
	Electrical/Electronic Applications		
	General Purpose		
	Telecommunications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.23	g/cm ³	ASTM D792
Spiral Flow	73.7	cm	
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2340	MPa	ASTM D638
Tensile Strength ² (Yield)	43.4	MPa	ASTM D638
Tensile Elongation ³ (Break)	15	%	ASTM D638
Flexural Modulus	2410	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256A
0°C, 3.18 mm, Injection Molded	53	J/m	
23°C, 3.18 mm, Injection Molded	110	J/m	

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	82.2	°C	
0.45 MPa, Annealed, 6.35 mm	92.2	°C	
1.8 MPa, Unannealed, 6.35 mm	77.8	°C	
1.8 MPa, Annealed, 6.35 mm	90.0	°C	
RTI Elec	50.0	°C	UL 746
RTI Imp	50.0	°C	UL 746
RTI Str	50.0	°C	UL 746
Flammability	Nominal Value		Test Method
	V-0		
Flame Rating (1.50 mm, ALL)	5VA	UL 94	
CSA Flammability ⁴			
1.47 mm	V-0		
1.55 mm	5VA		
Injection	Nominal Value	Unit	
Processing (Melt) Temp	204 to 210	°C	
NOTE			
1.	Type I, 51 mm/min		
2.	Type I, 51 mm/min		
3.	Type I, 51 mm/min		
4.	All Colors		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT