

Keyflex® BT 1140D

Thermoplastic Copolyester Elastomer

LG Chem Ltd.

Message:

Description

General Purpose, Medium Modulus

Application

Cable & Wire Jackets, Hose & Tubing

General Information			
UL YellowCard	E67171-564771		
Features	General Purpose		
Uses	Cable Jacketing		
	Hose		
	Tubing		
	Wire & Cable Applications		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/2.16 kg)	15	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.60 to 1.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	90		
Shore D	36		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break, 2.00 mm)	19.6	MPa	ASTM D638
Tensile Elongation ² (Break, 2.00 mm)	1000	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	58.8	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ⁴	118	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C, 6.40 mm	No Break		
23°C, 6.40 mm	No Break		
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed, 6.40 mm)	52.0	°C	ASTM D648, ISO 75-2/B
Peak Melting Temperature	170	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (1.00 mm)	26	kV/mm	ASTM D149
Comparative Tracking Index (CTI) ⁵	600	V	UL 746
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.010	%	
Rear Temperature	180 to 200	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	200 to 220	°C	
Nozzle Temperature	200 to 220	°C	
Processing (Melt) Temp	180 to 220	°C	
Mold Temperature	10.0 to 35.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.010	%	
Cylinder Zone 1 Temp.	180 to 200	°C	
Cylinder Zone 2 Temp.	190 to 210	°C	
Cylinder Zone 3 Temp.	190 to 210	°C	
Cylinder Zone 4 Temp.	190 to 210	°C	
Adapter Temperature	190 to 210	°C	
Melt Temperature	180 to 220	°C	
Die Temperature	180 to 200	°C	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	15 mm/min		
4.	50 mm/min		
5.	Solution A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT