

LNP™ LUBRICOMP™ DFL42 compound

Polycarbonate

SABIC Innovative Plastics

Message:

LNP* LUBRICOMP* DFL42 a compound based on Polycarbonate resin containing 10% Glass Fiber, 20% PTFE. Added feature of this material is: Wear Resistant.

Also known as: LNP* LUBRICOMP* Compound DFL-4042

Product reorder name: DFL42

General Information			
UL YellowCard	E121562-101343413		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Additive	PTFE Lubricant (20%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.40 to 0.60	%	
Across Flow : 24 hr	0.60 to 0.80	%	
Water Absorption			
24 hr, 50% RH	0.11	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4420	MPa	ASTM D638
--	4360	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	67.0	MPa	ASTM D638
Yield	65.0	MPa	ISO 527-2/5
Break ³	66.0	MPa	ASTM D638
Break	64.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	3.1	%	ASTM D638
Yield	3.0	%	ISO 527-2/5
Break ⁵	3.7	%	ASTM D638
Break	3.5	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	4090	MPa	ASTM D790

-- ⁷	3960	MPa	ISO 178
Flexural Stress			
--	108	MPa	ISO 178
Yield, 50.0 mm Span ⁸	112	MPa	ASTM D790
Break, 50.0 mm Span ⁹	111	MPa	ASTM D790
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.40		
vs. Itself - Static	0.50		
Wear Factor - Washer	28.5	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	110	J/m	ASTM D256
23°C ¹⁰	11	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	560	J/m	ASTM D4812
23°C ¹¹	35	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	16.9	J	ASTM D3763
--	3.40	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	143	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹²	143	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	138	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹³	137	°C	ISO 75-2/Af
CLTE			ASTM D696
Flow : -30 to 30°C	3.5E-5	cm/cm/°C	
Transverse : -30 to 30°C	7.2E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	310 to 321	°C	
Front Temperature	321 to 332	°C	
Processing (Melt) Temp	304 to 327	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		

3.	Type I, 5.0 mm/min
4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	1.3 mm/min
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

