

# Hylon® N1015L

Polyamide 66

Ravago Manufacturing Americas, LLC

Message:

Nylon 66, 15% Glass Filled

| General Information                               |                                  |                   |             |
|---------------------------------------------------|----------------------------------|-------------------|-------------|
| Filler / Reinforcement                            | Glass Fiber,15% Filler by Weight |                   |             |
| RoHS Compliance                                   | RoHS Compliant                   |                   |             |
| UL File Number                                    | E157012                          |                   |             |
| Physical                                          | Nominal Value                    | Unit              | Test Method |
| Density                                           | 1.24                             | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage - Flow (3.18 mm)                | 0.50 to 0.80                     | %                 | ISO 294-4   |
| Water Absorption (23°C, 24 hr)                    | 1.0                              | %                 | ISO 62      |
| Mechanical                                        | Nominal Value                    | Unit              | Test Method |
| Tensile Stress (Break)                            | 121                              | MPa               | ISO 527-2   |
| Tensile Strain (Break)                            | 2.5                              | %                 | ISO 527-2   |
| Flexural Modulus                                  | 5170                             | MPa               | ISO 178     |
| Flexural Stress                                   | 179                              | MPa               | ISO 178     |
| Impact                                            | Nominal Value                    | Unit              | Test Method |
| Notched Izod Impact Strength                      | 4.0                              | kJ/m <sup>2</sup> | ISO 180     |
| Thermal                                           | Nominal Value                    | Unit              | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 235                              | °C                | ISO 75-2/A  |
| Flammability                                      | Nominal Value                    | Test Method       |             |
| Flame Rating                                      |                                  |                   | UL 94       |
| 1.50 mm                                           | HB                               |                   |             |
| 3.00 mm                                           | HB                               |                   |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT