

LNP™ THERMOCOMP™ OF008 compound

Linear Polyphenylene Sulfide

SABIC Innovative Plastics

Message:

LNP THERMOCOMP OF008 is a compound based on PPS - Linear resin containing 40% Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound OF-1008

Product reorder name: OF008

General Information			
UL YellowCard	E121562-101283821	E121562-101284690	
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Linear Polymer Structure		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.70	g/cm³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.30	%	
Across Flow : 24 hr	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	14100	MPa	ASTM D638
Tensile Strength (Break)	140	MPa	ASTM D638
Tensile Elongation (Break)	1.6	%	ASTM D638
Flexural Modulus	14200	MPa	ASTM D790
Flexural Strength	234	MPa	ASTM D790
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.41		
vs. Itself - Static	0.50		
Wear Factor - Washer	373	10^-10 in^5-min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	96	J/m	ASTM D256
Unnotched Izod Impact (23°C)	530	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	264	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (0.450 mm, Testing by SABIC)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Rear Temperature	304 to 316	°C	
Middle Temperature	321 to 332	°C	

Front Temperature	332 to 343	°C
Processing (Melt) Temp	316 to 321	°C
Mold Temperature	138 to 166	°C
Back Pressure	0.172 to 0.344	MPa
Screw Speed	30 to 60	rpm

NOTE

1. 50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

