## S&E; PVC GA-1008

## Polyvinyl Chloride

S&E; Specialty Polymers, LLC

## Message:

S & E PVC GA-1008 is a polyvinyl chloride product. It is available in North America. Typical application areas are: wire and cable.

| General Information          |                             |         |             |
|------------------------------|-----------------------------|---------|-------------|
| Uses                         | Wire and cable applications |         |             |
|                              | Wire sheath                 |         |             |
|                              | Insulating material         |         |             |
|                              |                             |         |             |
| Appearance                   | Available colors            |         |             |
|                              | Natural color               |         |             |
| Forms                        | Particle                    |         |             |
|                              |                             | l loit  | Test Mathad |
| Physical                     | Nominal Value               | Unit    | Test Method |
| Specific Gravity             | 1.37                        | g/cm³   | ASTM D792   |
| Hardness                     | Nominal Value               | Unit    | Test Method |
| Durometer Hardness           |                             |         | ASTM D2240  |
| Shaw A                       | 91                          |         | ASTM D2240  |
| Shaw A, 15 seconds           | 86                          |         | ASTM D2240  |
| Elastomers                   | Nominal Value               | Unit    | Test Method |
| Tensile Stress (100% Strain) | 10.0                        | MPa     | ASTM D412   |
| Tensile Strength (Yield)     | 15.9                        | MPa     | ASTM D412   |
| Tensile Elongation (Break)   | 330                         | %       | ASTM D412   |
| Thermal                      | Nominal Value               | Unit    | Test Method |
| Brittleness Temperature      | -22.0                       | °C      | ASTM D746   |
| Electrical                   | Nominal Value               | Unit    | Test Method |
| Volume Resistivity           | 1.5E+13                     | ohms∙cm | ASTM D257   |
| Flammability                 | Nominal Value               | Unit    | Test Method |
| Oxygen Index                 | 25                          | %       | ASTM D2863  |
| Additional Information       |                             |         |             |

Suggested Stock Temperature: 370°FTemperature Rating: 80°CMin. Wall Thickness: 0.03 inches

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

