

Tarnamid® T- 27 GF25 M

Polyamide 6

Grupa Azoty S.A.

Message:

Tarnamid T-27 GF25M is tribological modified grade, which cause decrease coefficient of friction and wear.

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Good Wear Resistance		
	Low Friction		
Uses	Appliances		
	Automotive Applications		
	Electrical/Electronic Applications		
	Household Goods		
Appearance	Black		
	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	30.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	1.4	%	
Flow : 2.00 mm	1.2	%	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	210	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8400	MPa	ISO 527-2/1
Tensile Stress (Yield)	150	MPa	ISO 527-2/5
Tensile Strain (Break)	4.0	%	ISO 527-2/5
Flexural Modulus ¹	7300	MPa	ISO 178
Flexural Stress ²	220	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	52	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	7.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	210	°C	ISO 75-2/A
Vicat Softening Temperature	215	°C	ISO 306/B
Melting Temperature	221	°C	ISO 11357-3
Additional Information	Nominal Value		Test Method
ISO Type	PA6, MHR, 14-080, GF25Z		ISO 1874
Injection	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Suggested Max Moisture	< 0.10	%	
Suggested Max Regrind	50	%	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	60.0 to 80.0	°C	
Injection Pressure	80.0 to 110	MPa	
Injection Rate	Fast		
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

