

KOCETAL® UR304LOBK

Acetal (POM) Copolymer

Kolon Plastics, Inc.

Message:

KOCETAL® UR304LOBK is an Acetal (POM) Copolymer product. It is available in Asia Pacific, Europe, Latin America, or North America. Applications of KOCETAL® UR304LOBK include electrical/electronic applications and engineering/industrial parts.

Characteristics include:

Flame Rated

Impact Modified

Low to No Odor/Taste

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
	Low to No Odor		
Uses	Fasteners		
	Switches		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.7	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.24	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	60		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	44.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	120	%	ASTM D638
Flexural Modulus (23°C)	1800	MPa	ASTM D790
Flexural Strength (23°C)	59.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	120	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648A
0.45 MPa, Unannealed	145	°C	
1.8 MPa, Unannealed	82.0	°C	
Melting Temperature	166	°C	ASTM D1525
CLTE - Flow	1.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant	3.70		ASTM D150
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

