

Lucene™ LC100

Thermoplastic Polyolefin Elastomer

LG Chem Ltd.

Message:

LC100 is an ethylene-1-octene copolymer produced using LG Chem's metallocene polymerization catalyst and solution process technology. This resin is an excellent impact modifier for plastics and offers excellent performance in shoe sole application.

Applications:

General purpose thermoplastic elastomers, Polymer modification

Shoe sole, Sealing layer in packaging film

Performance:

Improved impact strength and toughness

Outstanding clarity

Excellent compression set and tear strength

General Information			
Features	Copolymer		
	Good Tear Strength		
	High Clarity		
Uses	Footwear		
	Packaging		
	Plastics Modification		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Density	0.903	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.2	g/10 min	ASTM D1238
Mooney Viscosity (ML 1+4, 121°C)	23	MU	ASTM D1646
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	91		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	38.0	MPa	ASTM D638
Tensile Elongation ² (Break)	660	%	ASTM D638
Flexural Modulus - 1% Secant	83.0	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³	87.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-31.0	°C	Internal Method
Melting Temperature (DSC)	96.0	°C	Internal Method
NOTE			
1.	510 mm/min		
2.	510 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

