Huafon JF-HSY-ADP1

Polyurethane

Huafon Group Co., Ltd.

Message:

PU Adhesive for High Solid Content PU Resin Characteristics PU adhesive with hydrolysis resistance

| General Information | | |
|-------------------------------|----------------------|------|
| Features | Aromatic | |
| | Hydrolysis Resistant | |
| | | |
| Uses | Adhesives | |
| Additional Information | Nominal Value | Unit |
| Solvents | DMF | |
| Uncured Properties | Nominal Value | Unit |
| Solids Content | 34 to 36 | % |
| Cured Properties | Nominal Value | Unit |
| Tensile Modulus (100% Secant) | 1.20 to 1.80 | MPa |
| Tensile Strength | > 10.0 | MPa |
| Tensile Elongation at Break | > 700 | % |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

