

# ELASTOSIL® R 755/60

Silicone

Wacker Chemie AG

## Message:

Silicone Rubber, HTV

Molded Parts, Technical, Plastics and Rubber Processing

Coating of Fabrics and Textiles, Technical Textiles

Molded Parts, Food Contact, Plastics and Rubber Processing

General Information	
Features	Food Contact Acceptable
Uses	Compounding
	Industrial Applications
Processing Method	Calendering
	Compression Molding
	Press Molding

Uncured Properties	Nominal Value	Unit	Test Method
Color	Opaque		
Density	1.18	g/cm <sup>3</sup>	ISO 1183
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	61		DIN 53505
Tensile Strength	7.80	MPa	DIN 53504
Tensile Elongation at Break	320	%	DIN 53504
Compression Set	20	%	DIN ISO 815-B
Tear Strength	16.0	kN/m	ASTM D624B
Rebound Resilience	54	%	DIN 53512

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 1342475533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT