

Starex TF-0930

Acrylonitrile Butadiene Styrene
SAMSUNG SDI CO., LTD.

Message:

Starex TF-0930 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: flame rated.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	25	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow : 3.20 mm	0.30 to 0.40	%	ASTM D955
Across Flow : 3.20 mm	0.60	%	ASTM D955
Flow : 3.20 mm	0.40	%	ISO 2577
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785, ISO 2039-2
Pencil Hardness ¹	2H		JIS K5401
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	2600	MPa	ASTM D638
--	2600	MPa	ISO 527-2/50
Tensile Strength			
Yield ³	61.0	MPa	ASTM D638
Yield	55.0	MPa	ISO 527-2/5
Break ⁴	52.0	MPa	ASTM D638
Break	47.0	MPa	ISO 527-2/50
Tensile Elongation			
Break ⁵	12	%	ASTM D638
Break	12	%	ISO 527-2/5
Flexural Modulus			
-- ⁶	2800	MPa	ASTM D790
-- ⁷	2600	MPa	ISO 178
Flexural Strength			
-- ⁸	93.0	MPa	ASTM D790
-- ⁹	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹⁰			ISO 179/1eA
-30°C	30	kJ/m ²	
23°C	2.0	kJ/m ²	

Notched Izod Impact			
23°C, 3.18 mm	20	J/m	ASTM D256
23°C, 6.35 mm	20	J/m	ASTM D256
-30°C ¹¹	30	kJ/m ²	ISO 180/1A
23°C ¹²	2.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			ASTM D256
23°C, 3.18 mm	290	J/m	
23°C, 6.35 mm	290	J/m	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed, 4.00 mm	103	°C	ISO 75-2/B
1.8 MPa, Unannealed, 6.40 mm	84.0	°C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm	84.0	°C	ISO 75-2/A
Vicat Softening Temperature	94.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.50 to 3.00 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature			
--	85.0	°C	
Desiccant Dryer	80.0	°C	
Drying Time			
--	2.0 to 4.0	hr	
Desiccant Dryer	2.0 to 3.0	hr	
Suggested Max Moisture	< 0.050	%	
Rear Temperature	190 to 200	°C	
Middle Temperature	210 to 220	°C	
Front Temperature	230 to 240	°C	
Nozzle Temperature	230	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	49.0 to 245	MPa	
Back Pressure	0.490 to 1.96	MPa	
Screw Speed	50 to 150	rpm	
NOTE			
1.	Condition: 500g		
2.	5.0 mm/min		
3.	5.0 mm/min		
4.	5.0 mm/min		
5.	5.0 mm/min		
6.	2.8 mm/min		
7.	2.0 mm/min		
8.	2.8 mm/min		
9.	2.0 mm/min		

10.	Thickness: 4 mm
11.	Thickness: 4 mm
12.	Thickness: 4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

