

# Ecdel™ 9967

Thermoplastic Elastomer  
Eastman Chemical Company

Message:

Ecdel™ elastomers are medical grade copolyester ethers (COPE). They offer the clarity, toughness, and chemical resistance needed in a variety of flexible packaging including medical applications. Ecdel™ elastomer 9967 may be injection molded or extruded. In addition, it may be extrusion blow molded or processed into tubing. Ecdel™ elastomers may be extrusion blow molded directly into bags or extruded into film for later fabrication into bags. This product has been CRADLE TO CRADLE CERTIFIED Silver.

The CRADLE TO CRADLE CERTIFIED Mark is a registered certification mark used under license through McDonough Braungart Design Chemistry (MBDC). MBDC is a global sustainability consulting and product certification firm. The CRADLE TO CRADLE® framework moves beyond the traditional goal of reducing the negative impacts of commerce ('eco-efficiency'), to a new paradigm of increasing its positive impacts ('eco-effectiveness'). At its core, Cradle to Cradle design perceives the safe and productive processes of nature's 'biological metabolism' as a model for developing a 'technical metabolism' flow of industrial materials. Product components can be designed for continuous recovery and reutilization as biological and technical nutrients within these metabolisms. For more information about MBDC and to obtain printable certificates for Eastman Copolyesters, visit [www.mbdc.com](http://www.mbdc.com). Choose Eastman Chemical Company under Company Name in C2C Certified products to display a list of our products.

General Information			
Features	Good Chemical Resistance		
	Good Flexibility		
	Good Sterilizability		
	Good Toughness		
	High Clarity		
	High Heat Resistance		
	Low Extractables		
Uses	Bags		
	Film		
	Medical/Healthcare Applications		
	Packaging		
	Personal Care		
	Pharmaceutical Packaging		
	Tubing		
Forms	Pellets		
Processing Method	Extrusion		
	Extrusion Blow Molding		
	Film Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Water Absorption (23°C, 24 hr)	0.40	%	ASTM D570

Inherent Viscosity <sup>1</sup> (23°C)	1.2		Internal Method
Heat of Fusion (23°C)	27.0	kJ/kg	ASTM E793
Tear Strength (23°C)	350	N	ASTM D1004
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 23°C	95		
Shore D, 23°C	55		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	170	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield, 23°C, 3.00 mm, Injection Molded <sup>2</sup>	13.0	MPa	
Break, 23°C, 2.00 mm <sup>3</sup>	23.0	MPa	
Tensile Elongation			ASTM D638
Yield, 23°C	38	%	
Break, 23°C	400	%	
Flexural Modulus (23°C)	150	MPa	ASTM D790
Coefficient of Friction	> 1.0		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	130	µm	
Secant Modulus			ASTM D882
Tangent, MD : 130 µm	197	MPa	
Tangent, TD : 130 µm	221	MPa	
Tensile Strength			ASTM D882
TD : Yield, 130 µm	11.2	MPa	
MD : Break, 130 µm	41.5	MPa	
TD : Break, 130 µm	18.1	MPa	
Tensile Elongation			ASTM D882
MD : Yield, 130 µm	46	%	
TD : Yield, 130 µm	20	%	
MD : Break, 130 µm	330	%	
TD : Break, 130 µm	> 550	%	
Oxygen Permeability (30°C, 130 µm)	940	cm <sup>3</sup> /m <sup>2</sup> /24 hr	ASTM D1434
Water Vapor Transmission Rate (38°C, 100% RH, 130 µm)	150	g/m <sup>2</sup> /24 hr	ASTM F372
Elastomers	Nominal Value	Unit	Test Method
Clash-Berg Modulus			ASTM D1043
-70°C	930	MPa	
-28°C	240	MPa	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (-40°C)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -75.0	°C	ASTM D746

Glass Transition Temperature	-3.00	°C	DSC
Vicat Softening Temperature	170	°C	ASTM D1525 <sup>4</sup>
Peak Melting Temperature	205	°C	ASTM D3418
Peak Crystallization Temperature (DSC)	140	°C	ASTM D3418
CLTE - Flow (23°C)	9.0E-5	cm/cm/°C	ASTM D696
Specific Heat			DSC
25°C <sup>5</sup>	1600	J/kg/°C	
100°C <sup>6</sup>	1800	J/kg/°C	
150°C <sup>7</sup>	2000	J/kg/°C	
175°C <sup>8</sup>	2300	J/kg/°C	
200°C <sup>9</sup>	3100	J/kg/°C	
225°C <sup>10</sup>	2300	J/kg/°C	
Thermal Conductivity (23°C)	0.19	W/m/K	ASTM C177
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 130 µm)	73		ASTM D2457
Transmittance			ASTM D1003
Total, 130 µm	94.0	%	
Regular, 130 µm	91.0	%	
Haze (130 µm)	1.0	%	ASTM D1003
NOTE			
1.	EMN-A-AC-G-V-1		
2.	Type I, 500 mm/min		
3.	Type IV, 500 mm/min		
4.	Loading 1 (10 N)		
5.	Solid		
6.	Solid		
7.	Solid		
8.	Solid		
9.	Transition, apparent specific heat, including the effects of the heat of fusion.		
10.	Melt		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT