

Ultradur® B 4300 G2 BK5110

Polybutylene Terephthalate

BASF Corporation

Message:

Ultradur B 4300 G2 BK5110 is a pigmented black, easy flowing injection molding PBT with 10% glass fiber reinforcement for rigid, tough, and dimensionally stable parts.

Applications

Typical applications include timer dials, toggles, knobs, parts for thermostats, oven-door handles, toaster housings and grills.

General Information			
UL YellowCard	E41871-233776	E36632-531667	
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Dimensional Stability		
	Good Flow		
	Good Toughness		
	High Rigidity		
Uses	Electrical/Electronic Applications		
	Handles		
	Housings		
	Knobs		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	16.0	cm³/10min	ISO 1133
Water Absorption			ISO 62
23°C, 24 hr	0.20	%	
Saturation, 23°C	0.40	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Viscosity Number (Reduced Viscosity)	116.0	ml/g	ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4200	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	85.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.5	%	ISO 527-2
Flexural Modulus (23°C)	4200	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	4.7	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	185	°C	ISO 75-2/A
Melting Temperature (DSC)	223	°C	ISO 3146
RTI Elec			UL 746
0.750 mm	130	°C	
1.50 mm	130	°C	
3.00 mm	130	°C	
RTI Imp			UL 746
0.750 mm	125	°C	
1.50 mm	125	°C	
3.00 mm	125	°C	
RTI Str			UL 746
0.750 mm	125	°C	
1.50 mm	125	°C	
3.00 mm	140	°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.040	%	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	60.0 to 100	°C	
Injection Pressure	3.50 to 12.5	MPa	
Injection Rate	Fast		
Back Pressure	< 1.00	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT