

Synres-Almoco AMC 2567

Thermoset Polyester

Synres-Almoco BV

Message:

Glass-fibre reinforced Polyester moulding compound
Outstanding mechanical strength similar to BMC/SMC, very good electrical isolation properties and dimensional stability, excellent processability
Primary application(s): Connectors, Bobbins, Housings, Mounting plates
This product meets the allowed upper limits for heavy metals and PCAs and also conforms to the requirements of the EU directives 2002/95 (RoHS), 2002/96 (WEEE) and 2006/122 (PFOS)

General Information	
Filler / Reinforcement	Glass Fiber
Features	Good Dimensional Stability
	Good Electrical Properties
	Good Processability
	Good Strength
Uses	Bobbins
	Connectors
	Housings
Agency Ratings	EU 2002/96/EC (WEEE)
	EU 2006/122/EC
RoHS Compliance	RoHS Compliant
Forms	Granules
Processing Method	Compression Molding
	Injection Molding
	Resin Transfer Molding

Physical	Nominal Value	Unit	Test Method
Density	2.00 to 2.20	g/cm ³	ISO 1183
Apparent Density	0.70 to 0.85	g/cm ³	ISO 60
Molding Shrinkage - Flow ¹	0.15 to 0.45	%	ISO 2577
Water Absorption (23°C, 24 hr)	< 0.30	%	ISO 62
Post Shrinkage ²	< 0.050	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2
Compression Molded	6000 to 9000	MPa	
Injection Molded	13000 to 15000	MPa	
Tensile Stress			ISO 527-2

Compression Molded	35.0 to 60.0	MPa	
Injection Molded	60.0 to 70.0	MPa	
Flexural Modulus			ISO 178
Compression Molded	8000 to 12000	MPa	
Injection Molded	8000 to 12000	MPa	
Flexural Stress			ISO 178
Compression Molded	80.0 to 100	MPa	
Injection Molded	120 to 140	MPa	
Compressive Stress	120 to 170	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
Compression Molded	2.5 to 3.5	kJ/m ²	
Injection Molded	3.5 to 5.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
Compression Molded	5.0 to 10	kJ/m ²	
Injection Molded	9.0 to 14	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
1.8 MPa, Unannealed	> 200	°C	ISO 75-2/A
8.0 MPa, Unannealed	100 to 120	°C	ISO 75-2/C
CLTE - Flow (50 to 100°C)	1.0E-5 to 2.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.90 to 1.1	W/m/K	ASTM E1461
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13 to 1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14 to 1.0E+15	ohms · cm	IEC 60093
Electric Strength	25 to 35	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
	6.00		
100 Hz	5.00		
	5.00		
1 MHz	4.00		
Dissipation Factor			IEC 60250
100 Hz	0.010 to 0.030		
1 MHz	0.010 to 0.030		
Arc Resistance	PLC 4		ASTM D495
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method

Flame Rating			UL 94
0.600 mm	V-1		
3.00 mm	V-0		
Glow Wire Flammability Index	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature	930	°C	IEC 60695-2-13

NOTE			
1.	Compression Molded		
2.	168 h / 110°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT