

Geon™ Vinyl Flexible B85B0

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™ Vinyl Flexible B85B0 is a Flexible Polyvinyl Chloride product. It can be processed by extrusion or injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ Vinyl Flexible B85B0 include bags/liners and sporting goods.

General Information			
Additive	Biocide		
Features	Medium Gloss		
Uses	Liners		
	Swimming Pools		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.3 to 1.7	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	85		
Shore A, 15 sec	79		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Break	16.2	MPa	
100% Strain	8.27	MPa	
Tensile Elongation ² (Break)	400	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ³	70.1	kN/m	ASTM D624
Compression Set (23°C, 22 hr)	28	%	ASTM D395
Clash-Berg Modulus			ASTM D1043
--	331	MPa	
-32°C	310	MPa	
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-36.1	°C	ASTM D746
Injection	Nominal Value	Unit	
Processing (Melt) Temp	188 to 199	°C	
Extrusion	Nominal Value	Unit	

Melt Temperature	174 to 179	°C
NOTE		
1.	510 mm/min	
2.	510 mm/min	
3.	Die C, 510 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

