

Akulon® F130

Polyamide 6
DSM Engineering Plastics

Message:

Akulon® F130 is a polyamide 6 (nylon 6) material. This product is available in Europe and is processed by film extrusion or extrusion. Akulon® The main characteristics of F130 are: medium viscosity.

General Information	
Features	Medium viscosity
Forms	Particle
Processing Method	Film extrusion
	Extrusion

Multi-Point Data	Specific Volume vs Temperature (ISO 11403-2)
	Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Viscosity Number	196	cm³/g	ISO 307

Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ISO 8295
With itself-dynamic, cast film	1.0		ISO 8295
With itself-static, cast film	1.5		ISO 8295

Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	50	µm	
Tensile Modulus ¹ (50 µm, Cast Film)	455	MPa	Internal method
Tensile Stress - MD			ISO 527-3
Yield, 50 µm, cast film	31.0	MPa	ISO 527-3
50 µm, cast film	82.0	MPa	ISO 527-3
Tensile Elongation - MD (Broken, 50 µm, cast film)	350	%	ISO 527-3
Trouser Tear Resistance - MD (50 µm, Cast Film)	32.0	N/mm	ISO 6383-1
Water Vapor Transmission Rate (23°C, 85% RH, 50 µm, cast film)	35	g/m²/24 hr	DIS 15106-1/-3
Oxygen Transmission Rate ²			DIS 15105-1/-2
0% RH : 23°C, 50.0 µm	26	cm³/m²/bar/24 hr	DIS 15105-1/-2
85% RH : 23°C, 50.0 µm	39	cm³/m²/bar/24 hr	DIS 15105-1/-2
Specific Heat Capacity			
--	1550	J/kg/°C	
Average: 20 to 150°C	2250	J/kg/°C	

Puncture Resistance (50.0 μm) ³	13.0	J/cm	Internal method
RSV - Formic Acid, 1g/100 ml	3.03		Internal method
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	9.0E-5	cm/cm/°C	ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Transmittance (50.0 μm, Cast Film)	83.0	%	Internal method
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (260°C)	810	Pa·s	Internal method
Additional Information	Nominal Value	Unit	Test Method

Processing parameters for cast film test specimen:

Extruder Temperature: 270°C

Die Temperature: 270°C

Chill Roll Temperature: 110°C

NOTE

1. 50 mm/min
2. Cast Film
3. Cast Film

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT