

Vydyne® 66J

Polyamide 66

Ascend Performance Materials Operations LLC

Message:

Vydyne 66J is a high-viscosity, heat-stabilized PA66 resin suitable for injection-molding and extrusion applications. It is available in natural color only. Vydyne 66J resin offers high strength, rigidity and toughness over a broad range of demanding applications and good fluid resistance to a wide variety of chemicals, solvents and oils.

Typical Applications/End Uses:

Typical uses include packaging films, monofilaments, bristles, rods, tubing, sheet and extruded profiles.

General Information	
UL YellowCard	E70062-249071
Additive	heat stabilizer
Features	Kosher certification
	Rigidity, high
	High strength
	Solvent resistance
	Good chemical resistance
	Gasoline resistance
	Oil resistance
	Thermal Stability
	Good toughness
	General
	Viscosity, High
Uses	Bar
	Films
	monofilament
	Industrial application
	Pipe fittings
	Sheet
	Profile
Agency Ratings	ASTM D 4066 PA0124
	ASTM D 6779 PA0124
	FDA 21 CFR 177.1500
	FED L-P-410A
	MIL M-20693B
	NSF 51
RoHS Compliance	RoHS compliance

UL File Number	E70062
Appearance	Natural color
Forms	Particle
Processing Method	Blow film Extrusion

Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Vertical flow direction: 23°C, 2.00mm	2.0	--	%	ISO 294-4
Flow direction: 23°C, 2.00mm	2.1	--	%	ISO 294-4
Water Absorption				ISO 62
Saturated, 23°C	8.5	--	%	ISO 62
Equilibrium, 23°C, 50% RH	2.5	--	%	ISO 62

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	2800	1800	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Yield, 23°C	85.0	55.0	MPa	ISO 527-2
Fracture, 23°C	55.0	70.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	5.0	20	%	ISO 527-2
Nominal Tensile Strain at Break (23°C)	> 25	> 150	%	ISO 527-2
Flexural Modulus (23°C)	3100	900	MPa	ISO 178
Flexural Strength (23°C)	90.0	30.0	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2

Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	6.0	6.0	kJ/m ²	ISO 179/1eA
23°C	6.0	25	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		ISO 179/1eU
23°C	No Break	No Break		ISO 179/1eU
Notched Izod Impact				ISO 180
-30°C	6.0	6.0	kJ/m ²	ISO 180
23°C	6.0	25	kJ/m ²	ISO 180

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	195	--	°C	ISO 75-2/B

1.8 MPa, not annealed	70.0	--	°C	ISO 75-2/A
Melting Temperature (DSC)	260	--	°C	ISO 3146
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C, 2.00mm	1.0E-4	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C, 2.00mm	1.0E-4	--	cm/cm/°C	ISO 11359-2
RTI Elec				UL 746
0.710 mm	140	--	°C	UL 746
1.50 mm	140	--	°C	UL 746
3.00 mm	140	--	°C	UL 746
RTI Imp				UL 746
0.710 mm	95.0	--	°C	UL 746
1.50 mm	110	--	°C	UL 746
3.00 mm	110	--	°C	UL 746
RTI				UL 746
0.710 mm	115	--	°C	UL 746
1.50 mm	125	--	°C	UL 746
3.00 mm	125	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Arc Resistance (3.00 mm)	PLC 6	--		ASTM D495
Comparative Tracking Index (3.00 mm)	400 - 599	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.710 mm	PLC 0	--		UL 746
1.50 mm	PLC 0	--		UL 746
3.00 mm	PLC 0	--		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.710 mm	PLC 4	--		UL 746
1.50 mm	PLC 4	--		UL 746
3.00 mm	PLC 4	--		UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.710 mm	HB	--		UL 94
1.50 mm	HB	--		UL 94
3.00 mm	HB	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.710 mm	825	--	°C	IEC 60695-2-12
1.50 mm	825	--	°C	IEC 60695-2-12

3.00 mm	825	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature				IEC 60695-2-13
0.710 mm	700	--	°C	IEC 60695-2-13
1.50 mm	700	--	°C	IEC 60695-2-13
3.00 mm	700	--	°C	IEC 60695-2-13
Extrusion	Dry	Unit		
Cylinder Zone 1 Temp.	250 - 295		°C	
Cylinder Zone 2 Temp.	250 - 295		°C	
Cylinder Zone 3 Temp.	250 - 295		°C	
Cylinder Zone 4 Temp.	250 - 295		°C	
Cylinder Zone 5 Temp.	250 - 295		°C	
Melt Temperature	270 - 295		°C	
Die Temperature	270 - 295		°C	
Extrusion instructions				

Recommended Extrusion Conditions: Melt Point: 260°C Melt Pressure: 3 to 17 MPa Blow Film Bath Temperature: 20°C to 80°C Chill Roll Temperature (Cast Film): 20°C to 80°C Screw Design: General Purpose or Barrier

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT