

ADDILENE H 211 V20

Polypropylene Homopolymer
ADDIPLAST

Message:

ADDILENE H 211 V20 is a Polypropylene Homopolymer (PP Homopolymer) material filled with 20% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Primary attribute of ADDILENE H 211 V20: Rigid.
Typical applications include:
Automotive
Appliances
Industrial Applications

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	High Rigidity		
Uses	Appliance Components		
	Automotive Applications		
	Automotive Interior Parts		
	Industrial Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	79		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	70.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	4000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	36	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	6.5	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	132	°C	ISO 75-2/Af
Vicat Softening Temperature	160	°C	ISO 306/A50
Melting Temperature (DSC)	165	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+ 14	ohms	IEC 60093
Volume Resistivity	1.0E+ 14	ohms · cm	IEC 60093

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

