

GPPC PS-350

High Impact Polystyrene

GPPC Chemical Co., Ltd.

Message:

GPPC PS-350 is a High Impact Polystyrene material. It is available in Asia Pacific or North America for injection molding.

Important attributes of GPPC PS-350 are:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- Impact Resistant

General Information			
UL YellowCard	E115332-219493		
Features	High Impact Resistance		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
UL File Number	E115332		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
200°C/5.0 kg	4.8	g/10 min	
230°C/3.8 kg	14	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	58		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.18 mm)	28.4	MPa	ASTM D638
Flexural Modulus ² (3.18 mm)	2060	MPa	ASTM D790
Flexural Strength ³ (3.18 mm)	47.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
3.18 mm	98	J/m	
6.35 mm	83	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	82.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.59 mm	HB		
3.18 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	

Processing (Melt) Temp	160 to 240	°C
Mold Temperature	35.0 to 65.0	°C

NOTE

1.	50 mm/min
2.	15 mm/min
3.	15 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

