

MITELA® HD8B

Phenol Formaldehyde Resin

Schwartz Technical Plastic

Message:

Type 77 - Spezial Qualität

Applications:

Bearing shells

Bearing collars

General Information			
Uses	Bearing		
Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	100	MPa	ISO 527-2
Fracture	180	MPa	ISO 527-2
Flexural Modulus	8000	MPa	ISO 178
Compressive Stress	320	MPa	ISO 604
Coefficient of Friction ¹ (vs. Steel - Dynamic)	0.20		
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact Strength	55	kJ/m ²	ISO 180
Additional Information			
Safe Temperature Range, permanent: 120°C			
NOTE			
1.	without lubrication		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT